

# Provel

State of the art  
O&P automation



## Provel Preforms

Provel preforms are molded of high performance polymers using state of the art process controls to provide superior mechanical properties and consistent forming.

### Check Sockets

Impact Modified SBC

CK18, 18 cm, clear (Oven 170°C, Target Temp 125°C)

CK25, 25 cm, clear (Oven 170°C, Target Temp 109°C)

### Definitive Sockets

High Impact Polypropylene Copolymer

CP18N, 18 cm, natural (Oven 220°C, Target Temp 165°C)

CP25N, 25 cm, natural (Oven 220°C, Target Temp 164°C with recommended heat shield)

## Provel Inc

Cle Elum WA 98922

509.857.2009

[www.provel.us](http://www.provel.us)

© 2017 Provel Inc